

Title	Weld steel structures in all positions using the self shielded flux cored arc welding processes		
Level	4	Credits	6

Purpose	<p>This unit standard covers welding of steel structures in all positions to AS/NZS 2980, or equivalent, using the self shielded flux cored arc welding (FCAWss) process.</p> <p>People credited with this unit standard are able to prepare to weld, and weld steel structures to industry standard in all positions using the FCAWss process; and inspect and repair FCAWss welds.</p>
----------------	--

Classification	Mechanical Engineering > Welding
-----------------------	----------------------------------

Available grade	Achieved
------------------------	----------

Guidance information

1 References

Health and Safety at Work Act 2015.

Health and Safety in Welding. Wellington: Department of Labour, 2006. Available from <http://www.worksafe.govt.nz/>.

AS/NZS 1554.1:2014, *Structural steel welding – Part 1: Welding of steel structures*.

AS/NZS 2980:2007, *Qualification of welders for fusion welding of steels*.

2 Definitions

Accepted industry practice – approved codes of practice and standardised procedures accepted by the wider mechanical engineering industry sectors as examples of best practice.

Industry standard – AS/NZS 2980:2007, or equivalent.

Steel – weldable low-carbon unalloyed (carbon-manganese) steel.

Welding procedure – written work instruction providing all the necessary technical details for a specific welding application.

Workplace procedures – procedures used by the organisation carrying out the work and applicable to the tasks being carried out. Examples are – standard operating procedures, safety procedures, equipment operating procedures, codes of practice, quality management practices and standards, procedures to comply with legislative and local body requirements.

3 Recommended for entry

Unit 30282, *Weld steel structures in the downhand positions using the gas shielded flux cored arc welding process*.

4 Related unit standards

This unit standard is one of a flux cored steel metal arc welding set:

Unit 30282, *Weld steel structures in the downhand positions using the gas shielded flux cored arc welding process* (Level 3); a structural welding standard for steel fabricators who weld downhand to a certified structural standard.

Unit 30277, *Weld steel structures in all positions using the gas shielded flux cored arc welding processes* (Level 4); a structural welding standard for steel fabricators who weld in all positions to a certified structural standard.

Unit 30275, *Weld steel structures in all positions using the self shielded flux cored arc welding processes* (Level 4); a structural welding standard for steel fabricators who weld in all positions to a certified structural standard.

5 Timeframe

All activities are expected to be completed within commercially acceptable timeframes.

Outcomes and performance criteria

Outcome 1

Prepare to weld steel in all positions using the FCAWss process.

Performance criteria

1.1 Equipment is selected to meet welding procedure requirements.

Range power source rating and duty cycle; wire feed system and gun; welding cables; work clamp.

1.2 Equipment is assembled and maintained ready for use in accordance with manufacturer's instructions.

Range wire feed system; gun liner, nozzle and contact tip; welding cables; work clamp.

1.3 Steel is prepared and assembled in accordance with welding procedure.

Range preparation and assembly – cleaning, providing root face where required, tack welding to correct alignment and preset.

1.4 Consumables are selected in accordance with welding procedure.

Range electrodes by specification and classification.

Outcome 2

Weld steel structures to industry standard in all positions using the FCAWss process.

Range material thickness – 8 to 16 mm;
welds – tee joints in 2F, 3F, and 4F positions, butt joints in 2G, 3G, and 4G positions.

Performance criteria

2.1 Workplace safety procedures are followed.

Range use of personal protective equipment, checking of equipment for faults, use of fume extraction equipment, elimination of risk of fire or explosion, protection from arc radiation.

2.2 Measures to minimise welding distortion are applied in accordance with accepted industry practice.

Range examples are – weld sequence, restraint, backstepping.

2.3 Welds are deposited on steel to industry standard and in accordance with welding procedure.

2.4 Welds are cleaned in accordance with accepted industry practice.

Outcome 3

Inspect and repair FCAWss steel welds.

Performance criteria

3.1 Weld imperfections are identified by visual examination and workshop tests.

Range examples of workshop tests are – nick break, fillet break-over, bend, macro examination. One workshop test is required for each weld from outcome 2.

3.2 Weld imperfections are compared to the permissible levels allowed by the industry standard.

3.3 A weld defect is repaired to industry standard.

Range one of the following positions 3F, 4F, 2G, 3G, 4G.

Planned review date	31 December 2022
----------------------------	------------------

Status information and last date for assessment for superseded versions

Process	Version	Date	Last Date for Assessment
Registration	1	20 July 2017	N/A

Consent and Moderation Requirements (CMR) reference	0013
--	------

This CMR can be accessed at <http://www.nzqa.govt.nz/framework/search/index.do>.

Comments on this unit standard

Please contact Competenz qualifications@competenz.org.nz if you wish to suggest changes to the content of this unit standard.